## **FITAPOR MM**

FITAPOR MM is a Wattle extract based on Mimosa.

## TYPICAL ANALYSIS

Appearance Light brown powder

pH (10 % solution)  $5.0 \pm 1.0$ 

## **PROPERTIES**

When used alone, FITAPOR MM gives a leather quite soft with fine touch.

It is recommended in retanning of chrome tanned small calf and side leather. Moreover it is used as a dispersing agent in dyeing. It is also used in retanning of glove leather, giving fulness without altering softness and elasticity.

The resulting dyeings are very bright and the leather is glazable.

To obtain burnish or brushed leather, we recommend to add FITAPOR MM at the end of the recipe, together with formic acid.

## APPLICATION

Light leather and side box: 3-4 %, based on shaved weight.

Chrome bovine for shoes and upholstery: 5-6 %, based on shaved weight.

When correctly stored, it is stable 36 months.

This sheet is a synthetic illustration of the product to enable the user to employ it at the best.

Properties and values are not, therefore, sales specifications.

Taking into account the several possibilities of application of this product, no warranty of the results is possible. **Expiry date refers to the product well closed in the original container, in fresh and dry area.** Some particularly sensitive products, when open, should be used rapidly.

Stir well before using the product, close tightly the container to preserve the properties.

Our technical service is at your disposal for any recommendation.